



TITLE:

# Synthesis of 8-Aryl-O-methylcyanidins and Their Usage for Dye-Sensitized Solar Cell Devices

AUTHOR(S):

Kimura, Yuki; Oyama, Kin-ichi; Murata, Yasujiro;  
Wakamiya, Atsushi; Yoshida, Kumi

---

CITATION:

Kimura, Yuki ...[et al]. Synthesis of 8-Aryl-O-methylcyanidins and Their Usage for Dye-Sensitized Solar Cell Devices. International Journal of Molecular Sciences 2017, 18(2): 427.

ISSUE DATE:

2017-02-16

URL:

<http://hdl.handle.net/2433/218629>

RIGHT:

© 2017 by the authors; licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution license (<http://creativecommons.org/licenses/by/4.0/>).



Article

# Synthesis of 8-Aryl-*O*-methylcyanidins and Their Usage for Dye-Sensitized Solar Cell Devices

Yuki Kimura <sup>1</sup>, Kin-ichi Oyama <sup>2</sup>, Yasujiro Murata <sup>3</sup>, Atsushi Wakamiya <sup>3</sup> and Kumi Yoshida <sup>1,\*</sup>

<sup>1</sup> Graduate School of Information Science, Nagoya University, Chikusa, Nagoya 464-8601, Japan; kimura.yuki@i.mbox.nagoya-u.ac.jp

<sup>2</sup> Chemical Instrumentation Facility, Research Center for Materials Science, Nagoya University, Chikusa, Nagoya 464-8602, Japan; oyama@cic.nagoya-u.ac.jp

<sup>3</sup> Institute for Chemical Research, Kyoto University, Gokasho, Uji, Kyoto 611-0011, Japan; yasujiro@scl.kyoto-u.ac.jp (Y.M.); wakamiya@scl.kyoto-u.ac.jp (A.W.)

\* Correspondence: yoshidak@is.nagoya-u.ac.jp; Tel.: +81-52-789-5638

Academic Editors: Nuno Mateus, Iva Fernandes and Maurizio Battino

Received: 24 December 2016; Accepted: 9 February 2017; Published: 16 February 2017

**Abstract:** Anthocyanins as natural pigments are colorful and environmentally compatible dyes for dye-sensitized solar cells (DSSCs). To increase the efficiency, we designed and synthesized unnatural *O*-methylflavonols and *O*-methylcyanidins that possess an aryl group at the 8-position. We synthesized *per*-*O*-methylquercetin from quercetin, then using selective demethylation prepared various *O*-methylquercetins. Using the Suzuki-Miyaura coupling reaction, 8-arylation of *per*-*O*-methylquercetin was achieved. Using a LiAlH<sub>4</sub> reduction or Clemmensen reduction, these flavonols were transformed to the corresponding cyanidin derivatives in satisfactory yields. Using these dyes, we fabricated DSSCs, and their efficiency was investigated. The efficiency of *tetra*-*O*-methylflavonol was 0.31%. However, the introduction of the 8-aryl residue increased the efficiency to 1.04%. In comparison to these flavonols, *O*-methylcyanidins exhibited a lower efficiency of 0.05% to 0.52%. The introduction of the 8-aryl group into the cyanidin derivatives did not result in a remarkable increase in the efficiency. These phenomena may be due to the poor fit of the HOMO-LUMO level of the dyes to the TiO<sub>2</sub> conduction band.

**Keywords:** 8-aryl-*O*-methylcyanidin; 8-aryl-*O*-methylquercetin; dye-sensitized solar cells; *O*-methylcyanidin; *O*-methylquercetin

## 1. Introduction

Anthocyanins are natural pigments that are widespread in higher plants, and the current number of isolated pigments are approaching one thousand [1–5]. The distinct characteristics of anthocyanins include their beautiful colors, with a wide variety of colors ranging from red to purple and blue in nature [1,5,6]. In addition, the color changes based on the pH of the media and the existence of co-pigments and/or metal ions [1–6]. Due to these properties, anthocyanins have been used as safe food colorants for a long time [7,8]. Recently, anthocyanins have attracted increasing attention as functional colorants for lifestyle-related diseases [9–11] and potential dyes for dye-sensitized solar cells (DSSCs) devices [12,13], which are next-generation solar cells with low production costs and flexibility. To expand these studies, development of an efficient synthetic procedure of dyes is essential.

To synthesize anthocyanins, the metal reduction of flavonols to their corresponding anthocyanidins (anthocyanins) has been previously reported in the early 20th century [14–16]. This synthetic route is very effective because the transformation is achieved in a single-step reaction without any protecting groups at the polyphenolic hydroxyl groups. A long time after those reports, Brouillard and his group reported the reduction of flavonols using Zn–Hg in 1995 [17]; however, the yield was

not satisfactory. We re-investigated this reaction procedure and improved the reaction conditions using Zn powder rather than Zn amalgam and reported that anthocyanins can be obtained in a yield of more than 80% [18]. Using this method, several anthocyanins including acylated anthocyanins can be obtained from the corresponding flavonols [18,19]. This method was expanded to synthesize unnatural anthocyanidins. For this purpose, we first synthesized various methylated quercetins [20] and 8-substituted quercetins [21]. After selective demethylation, the reduction of these flavonols afforded substituted cyanidins in good yields.


DSSCs studies using anthocyanins have been carried out by several groups [22–26] because anthocyanin contains no metal ions and is environmentally friendly. However, the efficiency  $\eta\%$  value of the DSSCs using pure anthocyanins and/or extracts from plants was low (i.e., approximately 1.0%) [22–25]. In 2013, Calogero et al. reported an efficiency of 2.2% using synthetic anthocyanidin [27]. We fabricated DSSCs using five pure natural anthocyanidin 3-O-glucosides with different chromophores and compared the color of the cells as well as their efficiencies [28]. These pigments resulted in beautiful cells that were blue due to petunidin 3-O-glucoside and purplish blue due to delphinidin 3-O-glucoside. However, the efficiency was still not high (i.e., approximately 1% to 1.4%) [28]. The time-dependent density functional theory (TD-DFT) calculations for the anthocyanidin dye model cluster systems (dye/(TiO<sub>2</sub>)<sub>38</sub>) revealed that both indirect (Type-I) and direct (Type-II) electron injection mechanisms may co-exist [28]. In addition, the highest occupied molecular orbital (HOMO)-the lowest unoccupied molecular orbital (LUMO) level of the dye may not match well with the conduction band of TiO<sub>2</sub>, which may result in low efficiency of the anthocyanin dye-based DSSCs. A preliminary calculation indicated that introduction of an aryl group at the 8-position may increase the HOMO level of the dye to match the conduction band of TiO<sub>2</sub>. Therefore, we designed 8-arylanthocyanidin for use as a DSSC dye. We synthesized *O*-methylquercetins and 8-aryl-*O*-methylquercetins from quercetin. The number of methyl moieties was varied by selective demethylation [20]. These methylquercetin derivatives were transformed to the corresponding *O*-methylcyanidins and 8-aryl-*O*-methylcyanidins via reduction. Using the synthesized derivatives, we fabricated DSSCs, and the photoelectric conversion efficiency was measured.

## 2. Results and Discussion

### 2.1. Synthesis of *O*-Methylquercetins

The synthetic strategy for various *O*-methylquercetins and *O*-methylcyanidins bearing an 8-aryl group is shown in Scheme 1. First, we prepare *per-O*-methylquercetin (2) via permethylation of quercetin (1), and then, various *O*-methylquercetins with different numbers of methyl moieties were prepared via regioselective demethylation. In addition, regioselective iodination afforded 8-iodo *per-O*-methylquercetin (3), and then, Suzuki-Miyaura coupling afforded 8-aryl-*O*-methylquercetins. The quercetin derivatives were reduced to yield the corresponding *O*-methylcyanidins. Using this scheme, quercetin and cyanidin derivatives with different numbers of *O*-methyl residues and varied 8-aryl groups were prepared.

3,5,7,3',4'-*penta-O*-methylquercetin (2) was prepared in 86% yield by permethylation of 1 using MeI and NaH in dimethylformamide (DMF) [20]. Based on our regioselective demethylation method via *per-O*-methylquercetin (2), 3,7,3',4'-*tetra-O*-methylquercetin (4), 3,7,4'-*tri-O*-methylquercetin (5), 3,7-*di-O*-methylquercetin (6), and 7-*O*-methylquercetin (7) were synthesized [20]. Demethylation of 2 with BBr<sub>3</sub> in MeCN at room temperature afforded 3,7,3',4'-*tetra-O*-methylquercetin (4) as the sole product in 98% yield due to neighboring group participation by the 4-carbonyl group. The regioselective demethylation to synthesize 3,7,4'-*tri-O*-methylquercetin (5) and 7-*O*-methylquercetin (7) was achieved by controlling the amount of BBr<sub>3</sub> as well as the reaction temperature. 5 was synthesized in 40% yield using 2.0 eq. of BBr<sub>3</sub> in CH<sub>2</sub>Cl<sub>2</sub> at −30 °C. In addition, 7 was prepared in 25% yield using 3.0 eq. of BBr<sub>3</sub> in CH<sub>2</sub>Cl<sub>2</sub> at 0 °C. 3,7-*di-O*-methylquercetin (6) was obtained in 83% yield from 4 using a combination of BCl<sub>3</sub> and *tetra*-butylammonium iodide (TBAI) in CH<sub>2</sub>Cl<sub>2</sub>.




**Scheme 1.** Synthetic plan of O-methylquercetins (2–16) and O-methylanthocyanidins (17–23). (a) MeI (29 eq.), NaH (7.6 eq.), DMF, 80 °C; (b) NIS (1.2 eq.), DMF, 70 °C; (c) BBr<sub>3</sub> (2.0 eq.), MeCN, rt; (d) BBr<sub>3</sub> (2.0 eq.), CH<sub>2</sub>Cl<sub>2</sub>, −30 °C; (e) BBr<sub>3</sub> (3.0 eq.), CH<sub>2</sub>Cl<sub>2</sub>, 0 °C; (f) BCl<sub>3</sub> (5.3 eq.), TBAI (5.3 eq.), CH<sub>2</sub>Cl<sub>2</sub>, −20 °C; (g) 8: phenylboronic acid (2.0 eq.), Pd(OAc)<sub>2</sub> (3.0 mol %), K<sub>3</sub>PO<sub>4</sub> (3.0 eq.), toluene, 100 °C; 9: 1-naphthaleneboronic acid (2.0 eq.), Pd(OAc)<sub>2</sub> (3.0 mol %), K<sub>3</sub>PO<sub>4</sub> (3.0 eq.), PPh<sub>3</sub> (3.0 mol %), CPME, 100 °C; 10: 4-(diphenylamino)phenylboronic acid (1.5 eq.), Pd(OAc)<sub>2</sub> (1.5 mol %), K<sub>2</sub>CO<sub>3</sub> (2.0 eq.), EtOH/H<sub>2</sub>O, 80 °C; (h) BBr<sub>3</sub> (3.0 eq.), CPME, 0 °C → rt; (i) BCl<sub>3</sub> (5.3 eq.), TBAI (5.3 eq.), CH<sub>2</sub>Cl<sub>2</sub>, −20 °C; (j) LiAlH<sub>4</sub> (4.0 eq.), THF, rt; (k) Zn, HCl-MeOH, 0 °C and then air, HCl-MeOH, rt.

8-Iodo-*per-O*-methylquercetin (3) was prepared in 90% yield from 2 using *N*-iodosuccinimide (NIS) at room temperature (rt) [21,29]. The Suzuki-Miyaura coupling reaction [30–32] of 3 with phenylboronic acid in the presence of Pd(OAc)<sub>2</sub> and K<sub>3</sub>PO<sub>4</sub> in toluene afforded 3,5,7,3',4'-

*penta-O*-methyl-8-phenylquercetin (**8**) in 90% yield [21]. For the coupling reaction of **3** with 1-naphthaleneboronic acid, the  $\text{PPh}_3$  ligand was required. The reaction in the presence of  $\text{Pd}(\text{OAc})_2$ ,  $\text{PPh}_3$ , and  $\text{K}_3\text{PO}_4$  in cyclopentyl methyl ether (CPME) afforded 3,5,7,3',4'-*penta-O*-methyl-8-(1-naphthyl)quercetin (**9**) in 69% yield [21]. The coupling reaction between **3** and 4-(diphenylamino)phenylboronic acid was conducted according to Liu's ligand-free conditions [33]. The reaction in the presence of  $\text{Pd}(\text{OAc})_2$  and  $\text{K}_2\text{CO}_3$  in EtOH/ $\text{H}_2\text{O}$  afforded 3,5,7,3',4'-*penta-O*-methyl-8-(4-(diphenylamino)phenyl)quercetin (**10**) in 80% yield [21].


The demethylation of 8-phenyl-*penta-O*-methylquercetin (**8**) was investigated based on the reaction from **2** to **4** using  $\text{BBr}_3$  [20]. A slightly modified reaction condition using CPME as the solvent resulted in a high yield. As shown in Table 1, 3,7,3',4'-*tetra-O*-methyl-8-phenylquercetin (**11**), 3,7,3',4'-*tetra-O*-methyl-8-(1-naphthyl)quercetin (**12**), and 3,7,3',4'-*tetra-O*-methyl-8-(4-(diphenylamino)-phenyl)quercetin (**13**) was obtained in 88%, 78%, and 87% yield, respectively. These results indicated that the reactivity of the 5-*O*-methyl group was the highest among the five methyl residues in **8–10**, as was found in **2**. As we reported [20], the subsequent demethylation reaction of the 3,7,3',4'-*tetra-O*-methyl derivatives (**11–13**) was carried out using  $\text{BCl}_3/\text{TBAI}$  (Table 2). These reaction conditions primarily yielded 3,7-*di-O*-methyl compounds. Demethylation of **11** afforded 3,7-*di-O*-methyl-8-phenylquercetin (**14**) in 85% yield. Using the same reaction conditions, 3,7-*di-O*-methyl-8-(1-naphthyl)quercetin (**15**) and 3,7-*di-O*-methyl-8-(4-(diphenylamino)phenyl)quercetin (**16**) were obtained in 62% and 82% yield, respectively.

Table 1. Synthesis of 3,7,3',4'-*tetra-O*-methylquercetins (**11–13**).

			
<i>penta-O</i> -Methylquercetin	R	<i>tetra-O</i> -Methylquercetin	Yield (%) <sup>a</sup>
8	phenyl	11	88
9	1-naphthyl	12	78
10	4-(diphenylamino)phenyl	13	87

<sup>a</sup> Isolated yield.

Table 2. Synthesis of 3,7-*di-O*-methylquercetins (**14–16**).

			
<i>tetra-O</i> -Methylquercetin	R	<i>di-O</i> -Methylquercetin	Yield (%) <sup>a</sup>
11	phenyl	14	85
12	1-naphthyl	15	62
13	4-(diphenylamino)phenyl	16	82

<sup>a</sup> Isolated yield.

## 2.2. Synthesis of *O*-Methylanthocyanidins

The as-prepared *O*-methylquercetins were transformed to cyanidin derivatives (Scheme 1). Our preliminary experiments suggested that Clemmensen-type reduction of 3,5,7,3',4'-*penta-*

O-methylquercetin (**2**) using Zn/HCl [18] resulted in a messy product, and the yield of 3,5,7,3',4'-penta-O-methylcyanidin (**17**) was low. The well-known transformation from penta-O-methylquercetin (**2**) to 3,5,7,3',4'-penta-O-methylcyanidin (**17**) using a combination of LiAlH<sub>4</sub> and an oxidant was first reported in 1968 [34,35]. At that time, a large amount of LiAlH<sub>4</sub> was used, and after the reduction, re-oxidation was carried out to afford anthocyanidins. We re-investigated the transformation reaction and found that the reduction of **2** with 4 eq. of LiAlH<sub>4</sub> at room temperature afforded **17** in 70% yield without any oxidant [21]. In addition, quercetin derivatives possessing a 5-OH structure were transformed to the corresponding cyanidin compounds via a Clemmensen-type reduction [18]. Therefore, in this study, we employed both reaction conditions depending on the structure of the substrate.

The transformation from 3,7,3',4'-tetra-O-methylquercetin (**4**) to 3,7,3',4'-tetra-O-methylanthocyanidin (**18**) was investigated (Table 3). **4** and Zn powder were mixed in HCl-MeOH-tetrahydrofuran (THF) at 0 °C for 30 min under an Ar atmosphere, and then, the reaction mixture was exposed to air overnight after Zn removal to afford 3,7,3',4'-tetra-O-methylcyanidin (**18**) as the only product in 83% yield. Transformation of **5**, **6**, and **14** using the same method afforded 3,7,4'-tri-O-methylcyanidin (**19**) and 3,7-di-O-methylcyanidin (**20**) and 3,7-di-O-methyl-8-phenylcyanidin (**24**) in 75%, 71%, and 38%, respectively (Table 3). It was demonstrated that our sequential reduction-oxidation anthocyanin synthesis using Zn could be applicable to O-methylquercetins. To prepare 8-aryl-3,5,7,3',4'-penta-O-methylcyanidins (**21–23**) from 8-aryl-3,5,7,3',4'-penta-O-methylquercetins (**8–10**), LiAlH<sub>4</sub> reduction was applied [21]. **8** in THF was added to 4 equiv. of LiAlH<sub>4</sub> and maintained at rt for 30 min. After purification by column chromatography, 8-phenyl-3,5,7,3',4'-penta-O-methylcyanidin (**21**) was obtained in 41% yield. Using the same procedure, 3,5,7,3',4'-penta-O-methyl-8-(1-naphthyl)cyanidin (**22**) and 3,5,7,3',4'-penta-O-methyl-8-(4-(diphenylamino)phenyl)cyanidin (**23**) were prepared from the corresponding O-methylquercetins (**9** and **10**) in 57% and 66% yields, respectively.

**Table 3.** Synthesis of O-methylanthocyanidins (**18–20**, **24**) using Zn. <sup>a</sup> Isolated yield.

<b>O-Methylquercetin</b>	<b>R</b>	<b>R<sup>1</sup></b>	<b>R<sup>2</sup></b>	<b>O-Methylanthocyanidin</b>	<b>Yield (%) <sup>a</sup></b>
4	H	Me	Me	18	83
5	H	H	Me	19	75
6	H	H	H	20	71
14	phenyl	H	H	24	38

### 2.3. Photovoltaic Property of DSSCs Using O-Methylquercetins

First, we fabricated DSSCs with five O-methylquercetins (**2**, **4–7**) where the number of methylations differed. Their photovoltaic properties with AM 1.5 irradiation are shown in Table 4. N719 was used as the standard dye. Although 4-*tert*-butylpyridine (TBP) was typically added to the electrolyte to increase *V*<sub>oc</sub> [36,37], preliminary experiments indicated that TBP (0.5 mM) did not provide good results. Therefore, we performed the experiment without TBP. The cells with penta-O-methylquercetin (**2**), tetra-O-methylquercetin (**4**) and tri-O-methylquercetins (**5**) possessed a pale yellow color, and the cells with di-O-methylquercetin (**6**) and mono-O-methylquercetins (**7**) were orange, indicating that these dyes may be adsorbed to TiO<sub>2</sub> with the dihydroxyl group of the B-ring. The efficiencies (*η*%) of the DSSCs of O-methylquercetins were not high (i.e., ranging from 0.09%–0.82%). Quercetin (**1**) and mono-O-methylquercetin (**7**) exhibited a similar efficiency (ca. 0.6%),



and the highest (i.e., 0.82%) efficiency was observed for *di-O*-methylquercetin (**6**). We proposed that methylation may increase the hydrophobicity of the compounds, which would result in an increase of the efficiency. However, this behavior was not observed. The incident photon-to-current conversion efficiency (IPCE) spectra indicated that these compounds only absorbed light energy shorter than 500 nm, and a peak was observed at approximately 400 nm at a maximum of 60% with *di-O*-methylquercetin (**6**).

**Table 4.** Photovoltaic properties of the dye-sensitized solar cells (DSSCs) sensitized with *O*-methyl quercetins (**1**, **2**, **4–7**) <sup>a,b</sup>.

Dye	Solvent	$J_{sc}$ (mA/cm <sup>2</sup> )	$V_{oc}$ (mV)	FF	$\eta$ (%)
<i>penta</i> -OMeQ ( <b>2</b> )	MeOH	0.45	390	0.56	0.09
<i>tetra</i> -OMeQ ( <b>4</b> )	MeOH	1.17	450	0.59	0.31
<i>tri</i> -OMeQ ( <b>5</b> )	MeOH	2.04	439	0.60	0.54
<i>di</i> -OMeQ ( <b>6</b> )	MeOH	4.65	445	0.40	0.82
<i>mono</i> -OMeQ ( <b>7</b> )	MeOH	3.60	424	0.40	0.62
quercetin ( <b>1</b> )	MeOH	3.09	459	0.43	0.60
N719	MeCN/ <i>tert</i> -BuOH	15.7	717	0.64	7.3

<sup>a</sup> Dyes were dissolved in MeOH with the concentration of 0.5 mM and immersed for 3 h; <sup>b</sup> For measurement of photovoltaic properties  $I^-/I_3^-$  was used as an electrolyte.

Because *O*-methylquercetins are flat molecules that most likely stack on each other followed by quenching the harvested energy via intermolecular charge transfer, a hindered residue was introduced to prevent this phenomenon. In addition, an aryl group at the 8-position of the quercetin chromophore was introduced as an electron-donating residue, which may increase HOMO level. Based on results from preliminary experiments, we chose the 8-phenyl, 8-naphthyl and 8-(4-(diphenylamino)phenyl)-residues for the substituents and prepared nine 8-aryl-*O*-methylquercetins (**8–16**) for use as DSSC dyes. The photovoltaic properties are shown in Table 5. Similar to the methylquercetins, the cell color of the *penta*-*O*-methyl derivatives and *tetra*-*O*-methyl derivatives were yellow, and the *di*-*O*-methyl compounds were orange. Among these compounds, the efficiency of 8-naphthyl-3,7,3',4'-*tetra*-*O*-methylquercetin (**12**) exhibited a high value of 1.04% (Table 5). Other 8-aryl-3,7,3',4'-*tetra*-*O*-methylquercetins also exhibited a higher  $\eta\%$  compared to that of *tetra*-*O*-methylquercetin (**4**). The efficiencies of the 8-aryl-3,7-*di*-*O*-methylquercetins (**14–16**) were 0.67%–0.88%, which is nearly the same as that of 3,7-*di*-*O*-methylquercetins (**6**). The introduction of the 8-aryl residue to 3,5,7,3',4'-*penta*-*O*-methylquercetin did not result in any increase in  $\eta\%$  and exhibited a very low efficiency of 0.03%–0.06%. For these nine compounds, the efficiency may be affected by a balance of many factors, such as the hydrophobicity, electron density, and the adsorption to TiO<sub>2</sub>, which may cause complicated results.

**Table 5.** Photovoltaic properties of the DSSCs sensitized with 8-aryl-*O*-methylquercetins (**8–16**) <sup>a,b</sup>.

Dye	Solvent	$J_{sc}$ (mA/cm <sup>2</sup> )	$V_{oc}$ (mV)	FF	$\eta$ (%)
8-aryl- <i>penta</i> -OMeQ					
8-phenyl ( <b>8</b> )	MeOH	0.21	257	0.59	0.03
8-naphthyl ( <b>9</b> )	MeOH	0.25	264	0.62	0.04
8-(4-(diphenylamino)phenyl) ( <b>10</b> )	MeOH	0.28	350	0.59	0.06
8-aryl- <i>tetra</i> -OMeQ					
8-phenyl ( <b>11</b> )	CH <sub>2</sub> Cl <sub>2</sub>	2.15	486	0.63	0.66
8-naphthyl ( <b>12</b> )	MeOH <sup>c</sup>	2.35	663	0.70	1.04
8-(4-(diphenylamino)phenyl) ( <b>13</b> )	CH <sub>2</sub> Cl <sub>2</sub>	2.96	535	0.55	0.87
8-aryl- <i>di</i> -OMeQ					
8-phenyl ( <b>14</b> )	MeOH	3.73	451	0.40	0.67
8-naphthyl ( <b>15</b> )	MeOH	4.55	436	0.44	0.88
8-(4-(diphenylamino)phenyl) ( <b>16</b> )	MeOH	4.75	345	0.47	0.77

<sup>a</sup> Dyes were dissolved in each solvent with the concentration of 0.5 mM and immersed for 3 h; <sup>b</sup> For measurement of photovoltaic properties  $I^-/I_3^-$  was used as an electrolyte; <sup>c</sup> TBP (4-*tert*-butylpyridine) was added to the electrolyte.

## 2.4. Photovoltaic Property of DSSCs Using O-Methylcyanidins

Using metal reduction and hydride reagent reduction, O-methylcyanidins (**17–24**) were prepared, and DSSCs were fabricated. Then, their photovoltaic properties were measured (Table 6). The cells of the DSSCs fabricated with *penta-* (**17**), *tetra-* (**18**) and *tri-O-*methylcyanidins (**19**), 8-aryl-3,5,7,3',4'-*penta-O-*methylcyanidins (**21–23**) were red, and the cell of the DSSCs fabricated with *di-O-*methylcyanidin (**20**) and 8-phenyl-3,7-*di-O-*methylcyanidin (**24**) were blue. The red color dyes may exist without a tight chemical adsorption of TiO<sub>2</sub>. In the case of the blue color dyes, they might be due to the bond formation between the catechol-type B-ring and Ti atoms in TiO<sub>2</sub> [28].

**Table 6.** Photovoltaic properties of the DSSCs sensitized with O-methylcyanidins (**17–24**)<sup>a,b</sup>.

Dye	$J_{sc}$ (mA/cm <sup>2</sup> )	$V_{oc}$ (mV)	FF	$\eta$ (%)
<i>penta</i> -OMeCy ( <b>17</b> )	0.55	281	0.50	0.08
<i>tetra</i> -OMeCy ( <b>18</b> )	0.71	284	0.63	0.13
<i>tri</i> -OMeCy ( <b>19</b> )	0.51	266	0.63	0.08
<i>di</i> -OMeCy ( <b>20</b> )	1.41	356	0.64	0.32
8-phenyl- <i>penta</i> -OMeCy ( <b>21</b> )	1.18	297	0.64	0.22
8-naphthyl- <i>penta</i> -OMeCy ( <b>22</b> )	0.58	346	0.60	0.12
8-(4-(diphenylamino)phenyl)- <i>penta</i> -OMeCy ( <b>23</b> )	0.29	272	0.59	0.05
8-phenyl- <i>di</i> -OMeCy ( <b>24</b> )	2.43	328	0.65	0.52

<sup>a</sup> Dyes were dissolved in MeCN with the concentration of 0.5 mM and immersed for 14 h; <sup>b</sup> For measurement of photovoltaic properties I<sup>−</sup>/I<sub>3</sub><sup>−</sup> was used as an electrolyte.

The efficiencies ( $\eta$ %) of the DSSCs of O-methylcyanidins (**17–19**, **21–23**) without the catechol moiety were quite low and ranged from 0.08% to 0.22%. These low efficiencies ( $\eta$ %) could be attributed to the fact that the adsorption amount might be low because of a lack of di-OH at B-ring chromophore. On the other hand, *di-O-*methylcyanidins (**20**, **24**) with the catechol moiety exhibited a higher value of  $\eta$ % (0.32% for **20**, 0.52% for **24**). This increase might be due to the bond formation between the catechol moiety and TiO<sub>2</sub>. Because the efficiency ( $\eta$ %) of 8-phenyl-3,7-*di-O-*methylcyanidin (**24**) was higher than that of 3,7-*di-O-*methylcyanidin (**20**), a substitution effect at the 8-position was confirmed. However, the efficiency ( $\eta$ % = 0.52) of **24** was lower than that ( $\eta$ % = 0.67) of the 8-phenyl-*di-O-*methylquercetin (**14**). These results indicated that the introduction of the electron-donating aryl group at the 8-position increased the efficiency ( $\eta$ %) of the DSSCs when the dyes bonded to TiO<sub>2</sub>.

## 3. Materials and Methods

### 3.1. General

The melting points were measured on a Yanaco Mp-S3 micro melting point apparatus and are uncorrected. The infrared (IR) spectra were recorded on a JASCO FT/IR-460Plus spectrometer, and the ultraviolet-visible (UV-Vis) absorption spectra were recorded on a JASCO V-560 spectrophotometer (JASCO, Sapporo, Japan, cell length: 10 mm). The <sup>1</sup>H and <sup>13</sup>C nuclear magnetic resonance (NMR) spectra were recorded on a JEOL JNM-ECA-500 spectrometer (JEOL, Tokyo, Japan). The chemical shifts are reported in ppm on the  $\delta$  scale relative to CDCl<sub>3</sub> ( $\delta$  = 7.26 for <sup>1</sup>H-NMR), CDCl<sub>3</sub> ( $\delta$  = 77.0 for <sup>13</sup>C-NMR), CD<sub>3</sub>OD ( $\delta$  = 3.31 for <sup>1</sup>H-NMR), CD<sub>3</sub>OD ( $\delta$  = 49.0 for <sup>13</sup>C-NMR), DMSO-*d*<sub>6</sub> ( $\delta$  = 2.49 for <sup>1</sup>H-NMR), and DMSO-*d*<sub>6</sub> ( $\delta$  = 39.5 for <sup>13</sup>C-NMR) as internal references. The signal patterns are as follows: s, singlet; brs, broad singlet; d, doublet; brd, broad doublet; t, triplet; m, multiplet. High-resolution mass spectra (HRMS) were recorded on a Bruker micrOTOF-QII (ESI) spectrometer. Analytical thin-layer chromatography (TLC) was performed on Merck precoated analytical plates (0.25 mm thick, silica gel 60 F254, MERCK MILLIPORE, Darmstadt, Germany). High-performance liquid chromatography (HPLC) was performed using a system equipped with JASCO PU-1580 pumps, an MD-1515 detector, HG-1580-32 mixer, and DG-580-35 degasser (JASCO). An Octadecylsilane (ODS) column (SunShell C18, 2.6  $\mu$ m, 2.1 inside diameter  $\times$  100 mm, ChromaNik Technologies, Osaka,



Japan) was eluted at 40 °C using linear gradient elution (0.2 mL/min) over 20 min from 10% to 90% aq. MeCN solution containing 0.5% trifluoroacetic acid (TFA). Flash silica gel chromatography was performed using silica gel PSQ60B (Fuji Silysia Chemical, Kasugai, Japan). All reagents were purchased from commercial sources. All reactions were performed under an argon (Ar) atmosphere unless otherwise noted.

To coat the TiO<sub>2</sub> paste (Solaronix Ti-Nanoxide, Aubonne, Switzerland) onto fluorine-doped tin oxide (FTO) glass plates (Astellatech Co., Ltd., Yokohama, Japan, 75 mm × 25 mm × 1.8 mm thick), screen-printing equipment (WHT3, Mino International, Ltd., Tokyo, Japan and HP-320, Newlong Seimitsu Kogyo Co., Ltd., Tokyo, Japan) was used. Calcination of the TiO<sub>2</sub>-coated FTO glass was performed using a furnace (FT-101W, Full-Tech Co., Ltd., Osaka, Japan). N719 (Aldrich, Tokyo, Japan, 95%) was used as the standard dye.

### 3.2. Synthesis of *O*-Methylquercetins

#### 3.2.1. 3,7,3',4'-tetra-*O*-Methyl-8-phenylquercetin (**11**)

To a solution of **8** (710 mg, 1.6 mmol) in cyclopentyl methyl ether (CPME) (20 mL) was added BBr<sub>3</sub> (4 mL, 4.0 mmol, 1.0 M solution in CH<sub>2</sub>Cl<sub>2</sub>) dropwise at 0 °C. After stirring for 5 min at 0 °C and for 60 min at rt, MeOH (25 mL) was poured into the mixture. The reaction mixture was concentrated under reduced pressure and saturated aq. NaCl (30 mL) was added. After the mixture was extracted with CH<sub>2</sub>Cl<sub>2</sub> (15 mL × 3), the combined organic phases were washed with saturated aq. NaCl (30 mL), dried over anhydrous Na<sub>2</sub>SO<sub>4</sub> and concentrated under reduced pressure. The crude product was recrystallized from AcOEt (20 mL) to give **11** as a yellow solid (607 mg, 88%). mp: 225–226 °C; IR (KBr) cm<sup>−1</sup>: 2995, 1585, 1517, 1267, 1217 cm<sup>−1</sup>; UV-Vis (CDCl<sub>3</sub>) λ<sub>max</sub> nm (ε): 276 nm (20,160), 366 nm (26,960); <sup>1</sup>H-NMR (CDCl<sub>3</sub>, 500 MHz) δ 3.61 (3H, s), 3.84 (3H, s), 3.90 (3H, s), 3.91 (3H, s), 6.50 (1H, s), 6.86 (1H, d, *J* = 9.0 Hz), 7.17 (1H, d, *J* = 2.5 Hz), 7.3–7.4 (3H, m), 7.4–7.5 (2H, m), 7.76 (1H, dd, *J* = 9.0, 2.5 Hz); <sup>13</sup>C-NMR (CDCl<sub>3</sub>, 125 MHz) δ 55.8, 55.9, 56.2, 60.0, 94.9, 105.4, 109.5, 110.3, 110.8, 122.7, 123.0, 127.3, 128.1, 131.2, 132.2, 138.8, 148.7, 151.2, 152.8, 155.3, 161.7, 162.3, 179.1; ESI-TOF HRMS Calcd. For C<sub>25</sub>H<sub>23</sub>O<sub>7</sub> [M + H]<sup>+</sup>, 435.1438; Found: 435.1440.

#### 3.2.2. 3,7,3',4'-tetra-*O*-Methyl-8-(1-naphthyl)quercetin (**12**)

According to the procedure described for **11**, the reaction of **9** (400 mg, 0.80 mmol) was carried out to afford **12** (304 mg, 78%) as a yellow solid. mp: 239–240 °C; IR (KBr) cm<sup>−1</sup>: 3437, 2935, 1648, 1589, 1218 cm<sup>−1</sup>; UV-Vis (CDCl<sub>3</sub>) λ<sub>max</sub> nm (ε): 275 nm (27,800), 364 nm (20,940); <sup>1</sup>H-NMR (CDCl<sub>3</sub>, 500 MHz) δ 3.16 (3H, s), 3.76 (3H, s), 3.83 (3H, s), 3.90 (3H, s), 6.58 (1H, s), 6.59 (1H, d, *J* = 2.5 Hz), 6.72 (1H, d, *J* = 8.5 Hz), 7.3–7.4 (1 H, m), 7.4–7.5 (2H, m), 7.5–7.6 (3H, m), 7.8–7.9 (2H, m); <sup>13</sup>C-NMR (CDCl<sub>3</sub>, 125 MHz) δ 55.2, 55.8, 56.2, 59.9, 95.0, 105.5, 107.2, 109.7, 110.6, 122.6, 122.8, 125.6, 125.9, 126.3, 128.1, 128.2, 129.0, 148.5, 151.0, 153.4, 155.4, 162.2, 163.1, 179.1; ESI-TOF HRMS Calcd. For C<sub>29</sub>H<sub>25</sub>O<sub>7</sub> [M + H]<sup>+</sup>, 485.1595; Found: 485.1592.

#### 3.2.3. 3,7,3',4'-tetra-*O*-Methyl-8-(4-(diphenylamino)phenyl)quercetin (**13**)

According to the procedure described for **11**, the reaction of **10** (210 mg, 0.34 mmol) was carried out to afford **13** (179 mg, 87%) as a yellow solid. mp: 260–261 °C; IR (KBr) cm<sup>−1</sup>: 3435, 2992, 1587, 1488, 1266 cm<sup>−1</sup>; UV-Vis (CDCl<sub>3</sub>) λ<sub>max</sub> nm (ε): 254 nm (24,060), 312 nm (39,080), 363 nm (16,600); <sup>1</sup>H-NMR (CDCl<sub>3</sub>, 500 MHz) δ 3.80 (3H, s), 3.87 (3H, s), 3.90 (3H, s), 3.95 (3H, s), 6.50 (1H, s), 6.87 (1H, d, *J* = 9.0 Hz), 7.0–7.3 (14H, m), 7.54 (1H, d, *J* = 2.0 Hz), 7.64 (1H, dd, *J* = 9.0, 2.0 Hz); <sup>13</sup>C-NMR (CDCl<sub>3</sub>, 125 MHz) δ 56.0, 56.2, 56.3, 60.1, 95.0, 105.5, 109.1, 110.7, 111.1, 122.5, 122.6, 123.1, 124.6, 125.5, 129.3, 131.9, 138.7, 146.8, 147.6, 148.7, 151.3, 153.0, 155.6, 161.5, 162.4, 179.1; ESI-TOF HRMS Calcd. For C<sub>37</sub>H<sub>32</sub>NO<sub>7</sub> [M+H]<sup>+</sup>, 602.2173; Found: 602.2177.

### 3.2.4. 3,7-di-O-Methyl-8-phenylquercetin (14)

To a solution of **11** (150 mg, 0.35 mmol) and tetrabutylammonium iodide (TBAI) (0.68 g, 1.83 mmol) in CH<sub>2</sub>Cl<sub>2</sub> (3 mL) was added BCl<sub>3</sub> (1.83 mL, 1.83 mmol, 1.0 M solution in CH<sub>2</sub>Cl<sub>2</sub>) dropwise at −20 °C. After stirring for 60 min at −20 °C, MeOH (4.5 mL) was poured into the mixture. The reaction mixture was concentrated under reduced pressure and saturated aq. Na<sub>2</sub>S<sub>2</sub>O<sub>3</sub> (20 mL) was added. After the mixture was extracted with AcOEt (15 mL × 3), the combined organic phases were washed with saturated aq. NaCl (20 mL), dried over anhydrous Na<sub>2</sub>SO<sub>4</sub> and concentrated under reduced pressure. The residue was purified by flash silica gel chromatography (*n*-hexane/AcOEt = 1:2 to AcOEt) to give **14** as a yellow solid (119 mg, 85%). mp: 261–262 °C; IR (KBr) cm<sup>−1</sup>: 3476, 1649, 1595, 1442, 1274 cm<sup>−1</sup>; UV-Vis (MeOH) λ<sub>max</sub> nm (ε): 258 nm (35,800), 372 nm (23,800); <sup>1</sup>H-NMR (DMSO-*d*<sub>6</sub>, 500 MHz) δ 3.80 (3H, s), 3.82 (3H, s), 6.66 (1H, s), 6.70 (1H, d, *J* = 8.5 Hz), 7.01 (1H, dd, *J* = 8.5, 2.5 Hz), 7.4–7.5 (6H, m), 9.19 (OH, brs), 9.80 (OH, brs); <sup>13</sup>C-NMR (DMSO-*d*<sub>6</sub>, 125 MHz) δ 56.4, 59.6, 95.2, 104.6, 108.9, 115.3, 115.9, 120.8, 127.3, 127.9, 131.1, 131.4, 137.5, 145.1, 148.7, 152.2, 156.0, 160.8, 161.9, 178.4; ESI-TOF HRMS Calcd. For C<sub>23</sub>H<sub>19</sub>O<sub>7</sub> [M + H]<sup>+</sup>, 407.1125; Found: 407.1133.

### 3.2.5. 3,7-di-O-Methyl-8-(1-naphthyl)quercetin (15)

According to the procedure described for **14**, the reaction of **12** (150 mg, 0.31 mmol) was carried out to afford **15** (88 mg, 62%) as a yellow solid. mp: 309–310 °C; IR (KBr) cm<sup>−1</sup>: 3479, 3152, 1601, 1438, 1207 cm<sup>−1</sup>; UV-Vis (MeOH) λ<sub>max</sub> nm (ε): 258 nm (41,060), 371 nm (29,600); <sup>1</sup>H-NMR (DMSO-*d*<sub>6</sub>, 500 MHz) δ 3.76 (3H, s), 3.80 (3H, s), 6.4–6.5 (2H, m), 6.75 (1H, s), 7.16 (1H, d, *J* = 2.0 Hz), 7.3–7.6 (6H, m), 8.0–8.1 (2H, m), 9.05 (OH, brs), 9.72 (OH, brs), 13.03 (OH, brs); <sup>13</sup>C-NMR (DMSO-*d*<sub>6</sub>, 125 MHz) δ 56.4, 59.6, 95.2, 104.8, 106.7, 115.1, 115.7, 119.6, 120.1, 125.2, 125.5, 125.7, 126.2, 128.0, 128.2, 129.1, 132.8, 137.4, 144.9, 148.6, 152.8, 155.7, 161.3, 162.6, 178.4; ESI-TOF HRMS Calcd. For C<sub>27</sub>H<sub>21</sub>O<sub>7</sub> [M + H]<sup>+</sup>, 457.1282; Found: 457.1280.

### 3.2.6. 3,7-di-O-Methyl-8-(4-(diphenylamino)phenyl)quercetin (16)

According to the procedure described for **14**, the reaction of **13** (150 mg, 0.25 mmol) was carried out to afford **16** (117 mg, 82%) as a yellow solid. mp: 271–272 °C; IR (KBr) cm<sup>−1</sup>: 3434, 1645, 1592, 1489, 1206 cm<sup>−1</sup>; UV-Vis (MeOH) λ<sub>max</sub> nm (ε): 257 nm (14,600), 304 nm (22,800), 368 nm (10,000); <sup>1</sup>H-NMR (DMSO-*d*<sub>6</sub>, 500 MHz) δ 3.80 (3H, s), 3.83 (3H, s), 6.63 (1H, s), 6.76 (1H, d, *J* = 8.0 Hz), 7.0–7.4 (15H, m), 7.47 (1H, d, *J* = 2.0 Hz), 9.24 (OH, brs), 9.91 (OH, brs), 13.0 (OH, brs); <sup>13</sup>C-NMR (DMSO-*d*<sub>6</sub>, 125 MHz) δ 56.5, 59.6, 95.1, 104.7, 108.5, 115.3, 116.0, 120.2, 120.9, 122.8, 123.0, 123.9, 125.6, 129.6, 132.1, 137.5, 145.2, 146.3, 147.2, 148.8, 152.4, 155.8, 160.6, 178.4; ESI-TOF HRMS Calcd. For C<sub>35</sub>H<sub>28</sub>NO<sub>7</sub> [M + H]<sup>+</sup>, 574.1860; Found: 574.1849.

## 3.3. Synthesis of O-Methylanthocyanidins

### 3.3.1. 3,7,3',4'-tetra-O-Methylcyanidin (18)

To a suspension of **4** (200 mg, 0.56 mmol) and Zn powder (2.0 g, 31 mmol) in anhydrous MeOH (8.0 mL) and anhydrous THF (2.0 mL) was added 4 N hydrogen chloride-methanol solution (10 mL) at 0 °C. After stirring for 30 min at 0 °C, Zn was removed by suction filtration. The filtrate solution was stirred under air for 20 h. After the reaction solution was added with water containing 0.5% trifluoroacetic acid (TFA) (100 mL), MeOH and THF were removed under reduced pressure. The residual aqueous solution was extracted with CH<sub>2</sub>Cl<sub>2</sub> (20 mL × 4). The combined organic phases were dried over anhydrous Na<sub>2</sub>SO<sub>4</sub> and concentrated under reduced pressure. The residue was purified by flash silica gel chromatography (33% AcOEt/Hexane with 0.5% TFA → AcOEt with 0.5% TFA → 5% MeOH/AcOEt with 0.5% TFA) to give **18** as a TFA salt (dark red) solid (210 mg, 83%). mp: 110–111 °C; IR (KBr) cm<sup>−1</sup>: 2935, 1613, 1589, 1319, 1209 cm<sup>−1</sup>; UV-Vis (0.1% HCl-MeOH) λ<sub>max</sub> nm (ε): 279 nm (18,000), 522 nm (26,600); <sup>1</sup>H-NMR (10% TFA-*d*-CDCl<sub>3</sub>, 500 MHz) δ 4.02 (3H, s), 4.05 (3H, s),

4.08 (3H,s), 4.23 (3H,s), 6.84 (1H, s), 6.95 (1H, s), 7.14 (1H, d,  $J = 9.0$  Hz), 7.97 (1H, d,  $J = 2.5$  Hz), 8.37 (1H, dd,  $J = 9.0, 2.5$  Hz), 8.79 (1H, s),  $^{13}\text{C}$ -NMR (10%TFA- $d$ - $\text{CDCl}_3$ , 125 MHz)  $\delta$  56.4, 56.6, 56.8, 57.8, 92.5, 103.3, 112.0, 112.8, 112.9, 120.9, 128.8, 130.3, 147.9, 149.4, 155.3, 155.6, 156.6, 162.6, 169.2; ESI-TOF HRMS Calcd. For  $\text{C}_{19}\text{H}_{19}\text{O}_6$   $[\text{M}]^+$ , 343.1176; Found: 343.1170.

### 3.3.2. 3,7,4'-tri-O-Methylcyanidin (19)

According to the procedure described for **18**, the reaction of **5** (200 mg, 0.58 mmol) was carried out to afford **19** (192 mg, 75%) as a TFA salt (dark red) solid. mp: 144–145 °C; IR (KBr)  $\text{cm}^{-1}$ : 3284, 1680, 1574, 1375, 1204  $\text{cm}^{-1}$ ; UV-Vis (0.1% HCl-MeOH)  $\lambda_{\text{max}}$  nm ( $\epsilon$ ): 280 nm (11,080), 525 nm (17,320);  $^1\text{H}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 500 MHz)  $\delta$  3.95 (3H, s), 3.98 (3H,s), 4.17 (3H,s), 6.66 (1H, d,  $J = 2.0$  Hz), 7.02 (1H, d,  $J = 2.0$  Hz), 7.03 (1H, d,  $J = 9.0$  Hz), 7.89 (1H, d,  $J = 2.0$  Hz), 8.14 (1H, dd,  $J = 9.0, 2.0$  Hz), 8.70 (1H, s),  $^{13}\text{C}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 125 MHz)  $\delta$  56.9, 57.5, 58.3, 92.7, 103.3, 112.9, 114.3, 117.8, 122.4, 127.9, 130.8, 148.6, 149.4, 156.7, 157.8, 163.8, 170.0; ESI-TOF HRMS Calcd. For  $\text{C}_{18}\text{H}_{17}\text{O}_6$   $[\text{M}]^+$ , 329.1020; Found: 329.1023.

### 3.3.3. 3,7-di-O-methylcyanidin (20).

According to the procedure described for **18**, the reaction of **6** (200 mg, 0.61 mmol) was carried out to afford **20** (183 mg, 71%) as a TFA salt (dark red) solid. mp: 121–122 °C; IR (KBr)  $\text{cm}^{-1}$ : 3419, 1682, 1455, 1210, 1128  $\text{cm}^{-1}$ ; UV-Vis (0.1% HCl-MeOH)  $\lambda_{\text{max}}$  nm ( $\epsilon$ ): 280 nm (9600), 527 nm (11,600);  $^1\text{H}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 500 MHz)  $\delta$  3.98 (3H, s), 4.18 (3H,s), 6.67 (1H, d,  $J = 2.0$  Hz), 6.98 (1H, d,  $J = 9.0$  Hz), 7.05 (1H, d,  $J = 2.0$  Hz), 8.04 (1H, d,  $J = 2.5$  Hz), 8.15 (1H, dd,  $J = 9.0, 2.5$  Hz), 8.68 (1H, s),  $^{13}\text{C}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 125 MHz)  $\delta$  57.4, 58.2, 92.6, 103.1, 113.6, 117.6, 118.7, 121.3, 128.6, 129.7, 147.6, 149.3, 156.6, 157.7, 164.5, 169.5; ESI-TOF HRMS Calcd. For  $\text{C}_{17}\text{H}_{15}\text{O}_6$   $[\text{M}]^+$ , 315.0863; Found: 315.0864.

### 3.3.4. 3,7-di-O-Methyl-8-phenylcyanidin (24)

According to the procedure described for **18**, the reaction of **14** (80 mg, 0.61 mmol) was carried out to afford **24** (38 mg, 38%) as a TFA salt (dark red) solid. mp: 250–251 °C; IR (KBr)  $\text{cm}^{-1}$ : 3408, 3107, 1679, 1207, 1142  $\text{cm}^{-1}$ ; UV-Vis (0.1% HCl-MeOH)  $\lambda_{\text{max}}$  nm ( $\epsilon$ ): 281 nm (7700), 538 nm (7100);  $^1\text{H}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 500 MHz)  $\delta$  3.98 (3H, s), 4.22 (3H,s), 6.82 (1H, d,  $J = 8.5$  Hz), 6.99 (1H, s), 7.4–7.6 (5H, m), 7.69 (1H, dd,  $J = 8.5, 2.0$  Hz), 7.85 (1H, d,  $J = 2.0$  Hz), 8.80 (1H, s),  $^{13}\text{C}$ -NMR (10%TFA- $d$ - $\text{CD}_3\text{OD}$ , 125 MHz)  $\delta$  57.5, 58.2, 92.3, 98.9, 111.5, 117.3, 119.6, 121.5, 128.2, 129.4, 129.6, 129.9, 131.6, 132.1, 147.4, 149.1, 165.8, 171.8; ESI-TOF HRMS Calcd. For  $\text{C}_{23}\text{H}_{19}\text{O}_6$   $[\text{M}]^+$ , 391.1176; Found: 391.1181.

## 3.4. Preparation of DSSCs

We prepared the DSSCs according to the method reported by Liu et al. with slight modifications [28,38].  $\text{TiO}_2$  films for use as photoanodes were prepared by screen-printing  $\text{TiO}_2$  pastes with different particle diameters (11–400 nm) onto F-doped  $\text{SnO}_2$  glass. After treating the glass with a  $\text{TiCl}_4$  solution, the films were calcined using the following temperature program: heat from room temperature (rt) to 200 °C for 15 min, from 200 to 500 °C for 15 min, hold at 500 °C for 30 min, and then cool to rt. The  $\text{TiO}_2$  electrodes were immersed in methanol or acetonitrile solution and then maintained at room temperature (rt) for or 18 h. After dye loading, the films were removed and rinsed with acetonitrile. The dye-loaded  $\text{TiO}_2$  electrodes were sandwiched between commercially available Pt counter electrodes (Geomatec Co., Ltd., Yokohama, Japan) with electrolyte filling the gap separated by a spacer (HIMILAN: DuPont-Mitsui Polychemicals Co., Ltd., Tokyo, Japan). The active area of the cells was 0.16  $\text{cm}^2$ . Iodide ( $\text{I}^-/\text{I}_3^-$ ), which is a commonly used electrolyte, was used as the electrolyte in this study [38]. 4-*tert*-Butylpyridine (TBP) was occasionally added. The thicknesses of the  $\text{TiO}_2$  films on the FTO glasses were measured after the performance evaluation using a SURFCOM 130A (ACCURETECH Co., Ltd., Tokyo, Japan). The average thickness was approximately  $10 \pm 1$   $\mu\text{m}$ .

### 3.5. Measurement of the Cell Properties

The measurement of the cell properties was performed according to a previously reported protocol [28,38]. The current–voltage ( $J$ – $V$ ) characteristics of the cells were measured using an AM 1.5 solar simulator (OTENTO-SUN III, Bunkoukeiki Co., Ltd., Tokyo, Japan). The data were collected by a source meter (Keithley 2400), and the light-to-electricity conversion efficiency ( $\eta$ ) was obtained from the following equation:  $\eta = (J_{sc} \times V_{oc} \times FF)/P_{in}$ , where  $J_{sc}$  is the short-circuit photocurrent density,  $V_{oc}$  is the open-circuit voltage,  $FF$  is the fill factor, and  $P_{in}$  is the incident radiation power. The incident monochromatic photon-to-current conversion efficiency (IPCE) spectra were measured using an IPCE measurement system (SM-250 hyper mono light system, Bunkoukeiki Co., Ltd.). The IPCE values were obtained by comparing the current ratio and the IPCE value of the reference cell at each wavelength. The light intensity of the illumination source was adjusted using standard silicon photodiodes, i.e., BS520 for  $J$ – $V$  characteristics and SiPD S1337-1010BQ for external quantum efficiency (EQE) measurements (Bunkoukeiki Co., Ltd.).

## 4. Conclusions

We designed and synthesized four *O*-methylcyanidins, as well as three types of 8-aryl-*O*-methylquercetins and cyanidins, including several new compounds. The introduction of the 8-aryl residue was established with a Suzuki-Miyaura coupling of 8-iodo-*per-O*-methylquercetin, and reduction of the quercetin derivatives to the corresponding cyanidin compounds was achieved in satisfactory yield. This synthetic route is very practical and efficient for the preparation of substituted flavonols and anthocyanidins. In the near future, the function of these compounds to prevent metabolic syndromes in humans will be studied. Using these flavonoids, we fabricated DSSCs and evaluated their photovoltaic efficiency. The efficiency was relatively low compared to that of natural flavonols and anthocyanins, which may be due to intermolecular stacking of the compounds, and the harvested energy may be quickly quenched before the electron reaches the electrode. Further molecular design and preparations are underway.

**Acknowledgments:** We acknowledge the financial support for doctoral students (Yuki Kimura) that was provided by the Graduate School of Information Science, Nagoya University. We are grateful to Segawa and Uchida of The University of Tokyo as well as Kondo and Kajiwarra of Nagoya University for their suggestions and fruitful discussions. This work was supported by a JSPS KAKENHI, Grant-in-Aid for Exploratory Research (No. 24651091) and the Collaborative Research Program of the Institute for Chemical Research, Kyoto University (grants #2013-37, #2014-40, #2015-53 and #2016-48).

**Author Contributions:** Yuki Kimura, Kin-ichi Oyama and Kumi Yoshida conceived and designed the experiments; Yuki Kimura performed the experiments; Yuki Kimura, Kin-ichi Oyama, Atsushi Wakamiya and Kumi Yoshida analyzed the data; Yasujiro Murata contributed analysis tools; Yuki Kimura, Kin-ichi Oyama and Kumi Yoshida wrote the manuscript.

**Conflicts of Interest:** The authors declare no conflict of interest.

## References

- Goto, T.; Kondo, T. Structure and molecular stacking of anthocyanins flower color variation. *Angew. Chem. Int. Ed. Engl.* **1991**, *30*, 17–33. [[CrossRef](#)]
- Strack, D.; Wray, V. The anthocyanins. In *The Flavonoids Advances in Research Science 1986*; Harborne, J.B., Ed.; Chapman & Hall: London, UK, 1994; pp. 1–19.
- Williams, C.A.; Grayer, R. Anthocyanins and other flavonoids. *Nat. Prod. Rep.* **2004**, *21*, 539–573. [[CrossRef](#)] [[PubMed](#)]
- Andersen, O.M.; Jordheim, M. The anthocyanins. In *Flavonoids, Chemistry, Biochemistry and Applications*; Andersen, O.M., Markham, K.R., Eds.; CPC Press: Boca Raton, FL, USA, 2006; pp. 471–551.
- Yoshida, K.; Mori, M.; Kondo, T. Blue flower color development by anthocyanins: From chemical structure to cell physiology. *Nat. Prod. Rep.* **2009**, *26*, 884–915. [[CrossRef](#)] [[PubMed](#)]
- Brouillard, R.; Dangles, O. Flavonoids and flower colour. In *The Flavonoids Advances in Research Science 1986*; Harborne, J.B., Ed.; Chapman & Hall: London, UK, 1994; pp. 569–586.



7. Markakis, P. *Anthocyanins as Food Colors*; Academic Press: New York, NY, USA, 1982.
8. Francis, F.J.; Markakis, P.C. Food colorants: Anthocyanins. *Crit. Rev. Food Sci. Nutr.* **1989**, *28*, 273–314. [[CrossRef](#)] [[PubMed](#)]
9. Tsuda, T. Regulation of adipocyte function by anthocyanins; possibility of preventing the metabolic syndrome. *J. Agric. Food Chem.* **2008**, *56*, 642–646. [[CrossRef](#)] [[PubMed](#)]
10. He, J.; Giusti, M.M. Anthocyanins: Natural colorants with health-promoting properties. *Rev. Food Sci. Technol.* **2010**, *1*, 163–187. [[CrossRef](#)] [[PubMed](#)]
11. Norberto, S.; Silva, S.; Meireles, M.; Faria, A.; Pintado, M.; Calhau, C. Blueberry anthocyanins in health promotion: A metabolic overview. *J. Funct. Foods* **2013**, *5*, 1518–1528. [[CrossRef](#)]
12. Hagfeldt, A.; Boschloo, G.; Kloo, L.; Pettersson, H. Dye-sensitized solar cells. *Chem. Rev.* **2010**, *110*, 6595–6663. [[CrossRef](#)] [[PubMed](#)]
13. Calogero, G.; Bartolotta, A.; Marco, G.D.; Carlo, A.D.; Bonaccorso, F. Vegetable-based dye-sensitized solar cells. *Chem. Soc. Rev.* **2015**, *44*, 3244–3294. [[CrossRef](#)] [[PubMed](#)]
14. Everest, A.E. The production of anthocyanins and anthocyanidins. *Proc. R. Soc. B.* **1914**, *87*, 444–452. [[CrossRef](#)]
15. Everest, A.E. The production of anthocyanins and anthocyanidins—Part II. *Proc. R. Soc. B.* **1914**, *88*, 326–332. [[CrossRef](#)]
16. Shibata, K.; Shibata, Y.; Kasiwagi, I. Study on anthocyanins; color variation in anthocyanins. *J. Am. Chem. Soc.* **1919**, *41*, 208–220. [[CrossRef](#)]
17. Elhabiri, M.; Figueiredo, P.; Fougereuse, A.; Brouillard, R. A convenient method for conversion of flavonols into anthocyanins. *Tetrahedron Lett.* **1995**, *36*, 4611–4614. [[CrossRef](#)]
18. Yoshida, K.; Kondo, T.; Oyama, K.-I. Process for the Preparation of Anthocyanidin Derivative. Japan Patent JP5382676, 8 January 2014.
19. Oyama, K.-I.; Kawaguchi, S.; Yoshida, K.; Kondo, T. Synthesis of pelargonidin 3-O-6''-O-acetyl- $\beta$ -D-glucopyranoside, an acylated anthocyanin, via the corresponding kaempferol glucoside. *Tetrahedron Lett.* **2007**, *48*, 6005–6009. [[CrossRef](#)]
20. Kimura, Y.; Kato, R.; Oyama, K.-I.; Kondo, T.; Yoshida, K. Efficient preparation of various O-methylquercetins by selective demethylation. *Nat. Prod. Commun.* **2016**, *11*, 957–961.
21. Kimura, Y.; Oyama, K.-I.; Kondo, T.; Yoshida, K. Synthesis of 8-aryl-3,5,7,3',4'-penta-O-methylcyanidins from the corresponding quercetin derivatives by reduction with LiAlH<sub>4</sub>. *Tetrahedron Lett.* **2017**, in press. [[CrossRef](#)]
22. Tennakone, K.; Kumara, G.R.R.A.; Kumarasighe, A.R.; Wijayantha, K.G.U.; Sirimanne, P.M. A dye-sensitized nano-porous solid-state photovoltaic cell. *Semicond. Sci. Technol.* **1995**, *10*, 1689–1693. [[CrossRef](#)]
23. Cherepy, N.J.; Smestad, G.P.; Grätzel, M.; Zhang, J.Z. Ultrafast electron injection: Implications for a photoelectrochemical cell utilizing an anthocyanin dye-sensitized TiO<sub>2</sub> nanocrystalline electrode. *J. Phys. Chem. B* **1997**, *101*, 9342–9351. [[CrossRef](#)]
24. Lai, W.H.; Su, Y.H.; Teoh, L.G.; Hon, M.H. Commercial and natural dyes as photosensitizers for a water-based dye-sensitized solar cell loaded with gold nanoparticles. *J. Photochem. Photobiol. A* **2008**, *195*, 307–313. [[CrossRef](#)]
25. Chien, C.-Y.; Hsu, B.-D. Optimization of the dye-sensitized solar cell with anthocyanin as photosensitizer. *Sol. Energy* **2013**, *98*, 203–211. [[CrossRef](#)]
26. Li, Y.; Ku, S.-H.; Chen, S.-M.; Ali, M.A.; AlHemaid, F.A.M. Photoelectrochemistry for red cabbage extract as natural dye to develop a dye-sensitized solar cells. *Int. J. Electrochem. Sci.* **2013**, *8*, 1237–1245.
27. Calogero, G.; Sinopoli, A.; Citro, I.; Marco, C.D.; Petrov, V.; Diniz, A.M.; Parola, A.J.; Pina, F. Synthetic analogues of anthocyanins as sensitizers for dye-sensitized solar cells. *Photochem. Photobiol. Sci.* **2013**, *148*, 883–894. [[CrossRef](#)] [[PubMed](#)]
28. Kimura, Y.; Maeda, T.; Iuchi, S.; Koga, N.; Murata, Y.; Wakamiya, A.; Yoshida, K. Characterization of dye-sensitized solar cells using five pure anthocyanidin 3-O-glucosides possessing different chromophores. *J. Photochem. Photobiol. A* **2017**, *335*, 230–238. [[CrossRef](#)]
29. Lu, K.; Chu, J.; Wang, H.; Fu, X.; Quan, D.; Ding, H.; Yao, Q.; Yu, P. Regiospecific iodination of flavonoids by N-iodosuccinimide under neutral conditions. *Tetrahedron Lett.* **2013**, *54*, 6345–6348. [[CrossRef](#)]
30. Miyaura, N.; Yanagi, T.; Suzuki, A. The palladium-catalyzed cross-coupling reaction of phenylboronic acid with haloarenes in the presence of bases. *Synth. Commun.* **1981**, *11*, 513–519. [[CrossRef](#)]

31. Miyaura, N.; Suzuki, A. Palladium-catalyzed cross-coupling reactions of organoboron compounds. *Chem. Rev.* **1995**, *95*, 2457–2483. [[CrossRef](#)]
32. Callam, C.S.; Lowary, T.L. Suzuki cross-coupling reactions: Synthesis of unsymmetrical biaryls in the organic laboratory. *J. Chem. Educ.* **2001**, *78*, 947–948. [[CrossRef](#)]
33. Liu, C.; Rao, X.; Song, X.; Qiu, J.; Jin, Z. Palladium-catalyzed ligand-free and aqueous Suzuki reaction for the construction of (hetero)aryl-substituted triphenylamine derivatives. *RSC Adv.* **2013**, *3*, 526–531. [[CrossRef](#)]
34. Jurd, L. Quinone oxidation of flavenes and flavan-3,4-diols. *Chem. Ind.* **1966**, *40*, 1683–1684.
35. Weiss, A.C., Jr.; Jurd, L. Synthesis of Flav-2-enes and Flav-3-enes. *Chem. Ind.* **1968**, *23*, 743–744.
36. Huang, S.Y.; Schlichthörl, G.; Nozik, A.J.; Grätzel, M.; Frank, A.J. Charge recombination in dye-sensitized nanocrystalline TiO<sub>2</sub> solar cells. *J. Phys. Chem. B* **1997**, *101*, 2576–2582. [[CrossRef](#)]
37. Zhang, K.; Zhang, S.; Sodeyama, K.; Yang, X.; Chen, H.; Yanagida, M.; Tateyama, Y.; Han, L.A. A new factor affecting the performance of dye-sensitized solar cells in the presence of 4-*tert*-butylpyridine. *Appl. Phys. Express* **2012**, *5*, 1–3. [[CrossRef](#)]
38. Liu, Y.; Lin, H.; Tamaki, K.; Nakazaki, J.; Nishiyama, C.; Uchida, S.; Segawa, H.; Li, J. Kinetics versus energetics in dye-sensitized solar cells based on an ethynyl-linked porphyrin heterodimer. *J. Phys. Chem. C* **2014**, *118*, 1426–1435. [[CrossRef](#)]



© 2017 by the authors; licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<http://creativecommons.org/licenses/by/4.0/>).